This is an electronic reprint of the original article.
This reprint may differ from the original in pagination and typographic detail.

Dmitriev, V.V.; Kosarev, I.V.; Krusius, M.; Ponarin, D.V.; Ruutu, V.M.H.; Volovik, G.E.
Stable spin precession at one half of equilibrium magnetization in superfluid $^3\text{He-B}$

Published in:
Physical Review Letters

DOI:
[10.1103/PhysRevLett.78.86](https://doi.org/10.1103/PhysRevLett.78.86)

Published: 01/01/1997

Document Version
Publisher's PDF, also known as Version of record

Please cite the original version:
Dmitriev, V. V., Kosarev, I. V., Krusius, M., Ponarin, D. V., Ruutu, V. M. H., & Volovik, G. E. (1997). Stable spin precession at one half of equilibrium magnetization in superfluid $^3\text{He-B}$. *Physical Review Letters*, 78(1), 86-89. <https://doi.org/10.1103/PhysRevLett.78.86>

This material is protected by copyright and other intellectual property rights, and duplication or sale of all or part of any of the repository collections is not permitted, except that material may be duplicated by you for your research use or educational purposes in electronic or print form. You must obtain permission for any other use. Electronic or print copies may not be offered, whether for sale or otherwise to anyone who is not an authorised user.

Stable Spin Precession at One Half of Equilibrium Magnetization in Superfluid $^3\text{He-B}$

V. V. Dmitriev,^{1,2} I. V. Kosarev,¹ M. Krusius,² D. V. Ponarin,¹

V. M. H. Ruutu,² and G. E. Volovik^{2,3}

¹*Kapitza Institute for Physical Problems, 117334 Moscow, Russia*

²*Low Temperature Laboratory, Helsinki University of Technology, 02150 Espoo, Finland*

³*Landau Institute for Theoretical Physics, 117334 Moscow, Russia*

(Received 10 June 1996; revised manuscript received 11 October 1996)

New modes of spin precession have been observed in superfluid $^3\text{He-B}$ with a precessing magnetization $M = pM_{\text{eq}}$, where $p = 1, \frac{1}{2}$, and ≈ 0 . These dynamic order parameter states are the first examples of stable precession with a magnetization different from the equilibrium value M_{eq} . The $p = \frac{1}{2}$ mode is the second example of a phase-coherent state of a spin superfluid. The new states can be excited close to T_c in the range $1 - T/T_c \lesssim 0.02$ where dissipation is low and the energy barriers between the different local minima of the spin-orbit energy are small. [S0031-9007(96)01929-1]

PACS numbers: 67.57.Lm, 76.60.-k

A number of stable states of coherent spin precession have been observed and identified in NMR experiments in the normal and B phases of liquid ^3He and in $^3\text{He-}^4\text{He}$ solutions [1–4]. Some of these states in $^3\text{He-B}$ display the same features of spontaneously broken symmetry that characterize quantum coherence in superfluids. Here the role of the supercurrent is played by the spin current. The main difference from a superfluid with a mass supercurrent is that in general the spin is not conserved. To stabilize a steady precessing state an external radiofrequency (rf) field has to be applied to compensate for spin relaxation. The smaller the dissipation, the smaller the rf field can be, and the closer the system is to the ideal coherent dynamic state of a spin superfluid.

In $^3\text{He-B}$ one such state is the homogeneously precessing domain (HPD) [1]. The spin-superfluid properties of the HPD are well known: its spin current displays the Josephson effect and it supports topological spin-current vortices and collective modes, which result from the spin rigidity of this coherent state [5,6]. In the HPD mode the magnetization $\mathbf{M} = \gamma\mathbf{S}$ ($\mathbf{S}$ is the spin density and γ the gyromagnetic ratio) precesses with the thermal equilibrium magnitude $\gamma S_{\text{eq}} = \chi H$, where χ is the magnetic susceptibility, and H the static magnetic field.

We report the observation of new precessing states in $^3\text{He-B}$. As opposed to the HPD, these states may have a fractional value of spin density $S = pS_{\text{eq}}$ and can be stabilized with continuous wave (cw) NMR close to the superfluid transition temperature T_c . In particular the *half-magnetization* (HM) states with $p = \frac{1}{2}$ should display the generic properties of a coherently precessing spin state if they will be stabilized well below T_c .

Experiments.—NMR measurements were carried out with nuclear demagnetization cryostats both in Helsinki and Moscow in cylindrical sample containers. In Helsinki the cell was from quartz with diameter $D = 5$ mm and length $L = 7$ mm while in Moscow the inside surface was covered with lamsan polyethylene foil (similar to

mylar) and the dimensions were $D = 3.7$ mm and $L = 4$ mm. The measurements were performed at pressures $P = 0$ –12 bars in magnetic fields $H = 73$ –284 Oe (or Larmor frequencies $\omega_L/2\pi = \gamma H/2\pi = 235$ –920 kHz), oriented parallel to the container axis. With cw NMR we monitor the in-phase dispersion ($\propto S_x = S_{\perp} \cos \phi$) and out-of-phase absorption ($\propto S_y = S_{\perp} \sin \phi$) signals. In Moscow pulsed NMR measurements were also performed and the field homogeneity was improved from $\delta H/H \sim 7 \times 10^{-4}$ in Helsinki to 5×10^{-5} . It was then found that a small applied field gradient did not change the results qualitatively.

In a large transverse rf field $H_{\text{rf}} \geq 0.01$ Oe the cw NMR line shape changes drastically at temperatures $T \gtrsim 0.98T_c$. In Fig. 1 the absorption and dispersion signals are shown, measured at fixed excitation frequency ω_{rf} during a slow sweep of H . The signals display discontinuities, which indicate transitions between different states of spin precession. The new states appear when the field is swept through resonance and the tipping angle β of the precessing magnetization is large. A different sequence of states is traversed when the sweep is towards increasing (Fig. 1) or decreasing field (Fig. 2). The transitions are mostly of first order: they are hysteretic with respect to the sweep direction. In Fig. 2 the signals have been recorded during a slow warm-up. The lowermost spectrum is outside the temperature region of the new states and represents the usual NMR mode, when spin waves are excited in the static texture of the order parameter. We call this the *spin wave* (SW) state [7]. At higher temperatures new states appear. To identify these we perform a combination of cw and pulsed NMR measurement to determine the value of the precessing magnetization. By measuring the cw absorption and dispersion spectra we also record the transverse component of the spin density $S_{\perp} = S \sin \beta = (S_x^2 + S_y^2)^{1/2}$ as a function of T , H_{rf} , and the frequency shift $\omega_{\text{rf}} - \omega_L$. The results are compared with analytical solutions or numerical simulation. In

do not essentially change the states except in the case of $p = 0$, when the magnitude of S is not determined by Eq. (2) but mainly by dissipation [9].

Half-magnetization modes.—We observe four NMR signatures which we ascribe to $p = \frac{1}{2}$ states: HM1, HM2, and HM3 appear at positive frequency shifts $\omega_{rf} > \omega_L$ (Fig. 2) and HM4 at negative shifts $\omega_{rf} < \omega_L$ (Fig. 1). Their identification as $p = \frac{1}{2}$ states is based on a measurement of the magnetization. At fixed H in the desired state we switch off the rf pumping. Immediately after that a 90° tipping pulse is applied and the FID signal is recorded (inset in Fig. 1). On comparing its amplitude with that of the FID obtained after a single 90° tipping pulse in normal ^3He we find that for *all* HM modes the amplitude ratio is 0.50 ± 0.03 and not dependent on the phase of the rf pulse. This means that before the pulse the magnetization is roughly along $\mathbf{H}$ and $S \approx \frac{1}{2}S_{eq}$. For *all* HM modes the FID duration is nearly the same as in normal ^3He . This implies that, when $H_{rf} = 0$, they all reduce to the same HM state which preserves its configuration during the FID.

These features of the HM1, HM3, and HM4 states are well reproduced in numerical simulation. It also shows that in the presence of the rf field they share similar properties: (i) They lie near the positive intersection of the $p = \frac{1}{2}$ circle with the vertical line in Fig. 3. (ii) There is a degeneracy in the orientation of the orbital momentum: $\mathbf{L} \perp \mathbf{H}$. (iii) The spin precesses with ω_{rf} while the order parameter axis $\hat{\mathbf{n}}$ precesses with $\frac{1}{2}\omega_{rf}$ (applies to aligned HM states in general). By minimizing the dipole and spectroscopic energies, $F = F_D(s_z, l_z) - (\omega_L - \omega_{rf})S_z - S_x H_{rf}/\gamma$, an analytic description can be derived for HM4 with $\omega_{rf} < \omega_L$, where [10]

$$F_D(s_z, l_z) = (\chi/10\gamma^2)\Omega_B^2 \times [1 + 2l_z^2 s_z^2 + (1 - l_z^2)(1 - s_z^2) - (2/3) \times (1 + l_z)(1 + s_z)\sqrt{(1 - l_z^2)(1 - s_z^2)}]. \quad (3)$$

Here $s_z = S_z/S$, $l_z = L_z/L$, and $\hat{\mathbf{z}} \parallel \mathbf{H}$. Ω_B is the Leggett frequency of $^3\text{He-B}$ [7]. At relatively large negative frequency shift the two local minima from Ref. [10] merge into one with

$$\sin \beta \approx (1 + w^2/4)^{-1/2}, \quad w = 15\omega_{rf}(\omega_{rf} - \omega_L)/2\Omega_B^2.$$

For $T/T_c > 0.995$ and $H - \omega_{rf}/\gamma > 0.05$ Oe one has $\beta \ll 1$, in agreement with our observation. Well below T_c this state should have similar coherent spin-superfluid properties as the HPD.

At positive frequency shifts the HM3 state appears as a saddle point of F in a narrow range of the field sweep where the phase of precession $\phi \approx \pi$ and $S_x < 0$ (Fig. 2). Numerically HM1 and HM3 are readily identified while HM2 is not. The small dispersion of HM1 in a wide region of field sweep is similar to that found numeri-

FIG. 4. Dispersion (S_x), absorption (S_y), and total spin (S), normalized to S_{eq} , from numerical simulation at two temperatures. The sweep towards decreasing field was started from $\gamma H > \omega_{rf}$, but new states appear when $\gamma H < \omega_{rf}$. The parameters are $P = 0$, $H_{rf} = 0.02$ Oe, $\omega_{rf}/2\pi = 460$ kHz, $T_1 = 0.1$ s. The same calculation gives for a sweep towards increasing field, starting from $\gamma H < \omega_{rf}$, the HM4 state, when $\gamma H > \omega_{rf}$, as seen in Fig. 1. Only spatially homogeneous order parameter states are considered in the simulation. Therefore the BS mode (or its mirror state at $\omega_{rf} > \gamma H$ [12]) appears here outside the region of the HM and ZM states.

cally in Fig. 4(a), but the two ranges of frequency shift are different. Such inconsistency may be due to spatial inhomogeneity which is not included in the simulation. For instance the field inhomogeneity ($\delta H \sim 0.02$ Oe in Fig. 2) becomes especially important when $H - \omega_{rf}/\gamma \sim \delta H$. In this case the sign of the frequency shift may vary within the sample and the precessing state may be spatially inhomogeneous. This may also be responsible for the unidentified features marked with A in Figs. 1 and 2.

Zero-magnetization mode.—The signature of the $p \approx 0$ state at positive frequency shift $\omega_{rf} > \omega_L$ is shown in Fig. 2. The identification of this state is again based on pulsed NMR measurement of the magnitude of S . From the ratio of the initial FID amplitudes one can conclude that in the ZM state the spin decreases from $\lesssim 0.3S_{eq}$ at small frequency shifts down to the noise level $\sim 0.02S_{eq}$ at larger shifts. At large frequency shifts the transverse spin is found to be $S_\perp \propto T_c - T$ and it does not depend on H_{rf} . Also the FID amplitude is found to vary with time such that we estimate $\beta \approx 20^\circ - 30^\circ$. All these features are reproduced in the numerical simulation. It furthermore shows that the relaxation of the magnitude of S after switching off the rf pumping is sufficiently slow so that pulsed NMR can be used for estimating S and that the ZM state remains stable at small negative frequency shifts [$H - \omega_{rf}/\gamma \lesssim 0.1$ Oe for the conditions of Fig. 4(b)]. Thus the region marked by A in Fig. 1(a) might also

correspond to the ZM state. In Ref. [9] a state with $p \approx 0$ has been discussed analytically. There $\mathbf{L}$ was assumed to be $\parallel \mathbf{H}$, but the simulation shows that $\mathbf{L}$ prefers to be $\perp \mathbf{H}$.

Brinkman-Smith mode.—In the HPD mode spin currents maintain phase coherence of the spin precession and $\beta \geq \theta_L$, where $\theta_L \approx 104^\circ$ is the Leggett angle [7]. The precursor of the HPD, the *Brinkman-Smith* state (BS) [8], with $\beta < \theta_L$, was actually the first of the extraordinary precessing states which was observed in early pulsed NMR experiments [14]. Here we find for the first time that the BS mode can be stabilized in cw NMR [Fig. 1(b)]. In this case $\mathbf{S}$ is oriented along $\hat{\mathbf{H}}$ in the rotating frame [11,12], $\mathbf{S} \approx S_{\text{eq}} \hat{\mathbf{H}}/\hat{H}$ and $\sin \beta = H_{\text{rf}}/\hat{H}$. Experimentally the BS mode is identified by its transverse spin density $S_{\perp} = S_{\text{eq}} \sin \beta$, which was found to be in perfect agreement with the prediction.

A transition between any two states in Fig. 3, which involves a reorientation of $\mathbf{L}$, corresponds to a textural transformation. In the BS state the dipole energy orients $\mathbf{L}$ along $\mathbf{H}$ and the $\text{SW} \rightarrow \text{BS}$ or $\text{BS} \rightarrow \text{SW}$ transitions are to be accompanied by first order textural transformations. An anomaly observed in pulsed NMR measurements in Ref. [15] is explained by the $\text{SW} \rightarrow \text{BS}$ transition, as proposed in Ref. [16]. We observe the opposite case $\text{BS} \rightarrow \text{SW}$ [Fig. 1(b)] while the $\text{SW} \rightarrow \text{BS}$ transition is obscured by unidentified features at a small frequency shift where the SW mode becomes unstable.

There are differences in the results measured with the two sample cells. The ZM mode has been observed in both cylinders, but the HM modes were observed only in the lavsan-coated cell while the BS state was stable only in the quartz cell. This may be caused by the cylinder dimensions, field inhomogeneity, or relaxation at the walls. The effective longitudinal relaxation time T_1 was measured to be 1 min in the quartz and 1 s in the lavsan cells at $T \geq T_c$ ($P = 0$). In the simulation it is lumped into an effective bulk T_1 . The stable ranges of the new states were found to be sensitive to the choice of T_1 . A further possibility is that a textural transformation to the BS state triggers a transition to the HM or ZM states in the lavsan container. It has a smaller volume by a factor of 5 and perhaps the latter modes can more readily be created uniformly in this case.

In conclusion, we have observed the first examples of stable dynamic spin modes with a well-defined precessing magnetization which differs from the thermal equilibrium value. The existence of such modes had been proposed before theoretically [9,10], but it was not known in what

conditions they might be stabilized. It is now clear that they appear after crossing the resonance at $\omega_{\text{rf}} = \omega_L$ at a high rf level so that $\mathbf{S}$ is deflected by a large amount ($\beta \sim 180^\circ$). Simultaneously the HPD mode with $\mathbf{L} \parallel \mathbf{H}$ should be unstable towards a reorientation to $\mathbf{L} \perp \mathbf{H}$. Well below T_c this instability is difficult to reach due to the dipole torque and Leggett-Takagi dissipation, which rapidly grow with increasing β above θ_L . Numerical simulation of the resonance conditions from Leggett's spin dynamic equations also confirms that the new states can be reached in the vicinity of T_c where $F_D \propto T_c - T$ is small and the more conventional modes with $S = S_{\text{eq}}$ become unstable already with tipping angles $\beta < 180^\circ$ and, in fact, with β as small as $\sim 140^\circ$.

-
- [1] A. Borovik-Romanov, Yu. Bunkov, V. Dmitriev, and Yu. Mukharsky, JETP Lett. **40**, 1033 (1984); I. Fomin, *ibid.* **40**, 1037 (1984).
 - [2] Yu. Bunkov, S. Fisher, A. Guénault, G. Pickett, and S. Zakazov, Physica (Amsterdam) **194B**, 827 (1994).
 - [3] G. Nunes, C. Jin, D. Hawthorne, A. Putnam, and D. Lee, Phys. Rev. B **46**, 9082 (1992); H. Akimoto, O. Ishikawa, G. Oh, M. Nakagawa, T. Hata, and T. Kodama, J. Low Temp. Phys. **82**, 295 (1991).
 - [4] V. Dmitriev and I. Fomin, JETP Lett. **59**, 378 (1994); V. Dmitriev, V. Moroz, and S. Zakazov, J. Low Temp. Phys. **101**, 141 (1995).
 - [5] I. Fomin, Physica (Amsterdam) **169B**, 153 (1991).
 - [6] Yu. Bunkov, in *Progress in Low Temperature Physics*, edited by W. Halperin (Elsevier, Amsterdam, 1995), Vol. 14, p. 69.
 - [7] D. Vollhardt and P. Wölfle, *The Superfluid Phases of ^3He* (Taylor & Francis, London, 1990).
 - [8] W. Brinkman and H. Smith, Phys. Lett. **53A**, 43 (1975).
 - [9] E. Sonin, Sov. Phys. JETP **67**, 1791 (1988).
 - [10] G. Kharadze and G. Vachnadze, JETP Lett. **56**, 458 (1992).
 - [11] G. Volovik, J. Phys. Condens. Matter **5**, 1759 (1993).
 - [12] I. Fomin, in *Sov. Sci. Rev. Sec. A: Phys. Rev.* (Harwood Acad. Publ., Chur, 1981), Vol. 3, pp. 305–308.
 - [13] I. Fomin, J. Low Temp. Phys. **31**, 509 (1978).
 - [14] D. Osheroff and L. Corruccini, in *Proceedings of the 14th International Conference on Low Temperature Physics* (Elsevier, Amsterdam, 1975), Vol. 1, p. 100.
 - [15] A. Borovik-Romanov, Yu. Bunkov, V. Dmitriev, and Yu. Mukharskii, JETP Lett. **37**, 716 (1983).
 - [16] V. Golo, A. Leman, and I. Fomin, JETP Lett. **38**, 146 (1983).